

FORM-PTO-1390
(Rev. 9-2001)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371**

032326-179

U.S. APPLICATION NO. (if known, see 37 C.F.R. 1.51)

Unassigned

10/018089

INTERNATIONAL APPLICATION NO.
PCT/FR00/01488

INTERNATIONAL FILING DATE
30 May 2000

PRIORITY DATE CLAIMED
15 June 1999

TITLE OF INVENTION

NOVEL LINEAR BIODEGRADABLE COPOLYMER, COMPOSITION COMPRISING SAME, USE OF SAID COPOLYMER
AND SAID COMPOSITION

APPLICANT(S) FOR DO/EO/US

Christian LERICHE, Henri BOCCIA and Isabelle LIMOUSIN

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:


1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.
4. ☐ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☐ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11 to 20 below concern document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A FIRST preliminary amendment.
14. ☐ A SECOND or SUBSEQUENT preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
18. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
19. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
20. ☐ Other items or information:



21839

U.S. APPLICATION NO. (if known, see 37 C.F.R. 1.5)		INTERNATIONAL APPLICATION NO		ATTORNEY'S DOCKET NUMBER		
Unassigned 10/018089		PCT/FR00/01488		032326-179		
21. <input checked="" type="checkbox"/> The following fees are submitted: Basic National Fee (37 CFR 1.492(a)(1)-(5)): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1,040.00 (960) International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$890.00 (970) International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$740.00 (958) International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$710.00 (956) International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00 (962)				CALCULATIONS		PCT USE ONLY
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$ 890.00		
Surcharge of \$130.00 (154) for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.452(i)).				20 <input type="checkbox"/> 30 <input type="checkbox"/>	\$ -0-	
Claims	Number Filed	Number Extra	Rate			
Total Claims	21 -20 =	1	X\$18.00 (966)	\$ 18.00		
Independent Claims	1 -3 =	-0-	X\$84.00 (964)	\$ -0-		
Multiple dependent claim(s) (if applicable)				+ \$280.00 (968)	\$ -0-	
TOTAL OF ABOVE CALCULATIONS =				\$ 908.00		
Reduction for 1/2 for filing by small entity, if applicable (see below).				+ \$ -0-	-	
SUBTOTAL =				\$ 908.00		
Processing fee of \$130.00 (156) for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.452(i)).				20 <input type="checkbox"/> 30 <input type="checkbox"/>	\$ -0-	
TOTAL NATIONAL FEE =				\$ -0-		
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 (581) per property				+ \$ -0-	\$ -0-	
TOTAL FEES ENCLOSED =				\$ 908.00		
				Amount to be refunded:	\$	
				charged:	\$	
<p>a. <input type="checkbox"/> Small entity status is hereby claimed.</p> <p>b. <input checked="" type="checkbox"/> A check in the amount of \$ <u>908.00</u> to cover the above fees is enclosed.</p> <p>c. <input type="checkbox"/> Please charge my Deposit Account No. <u>02-4800</u> in the amount of \$_____ to cover the above fees. A duplicate copy of this sheet is enclosed.</p> <p>d. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>02-4800</u>. A duplicate copy of this sheet is enclosed.</p> <p>NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.</p>						
<p>SEND ALL CORRESPONDENCE TO:</p> <p>James A. LaBarre BURNS, DOANE, SWECKER & MATHIS, L.L.P. P.O. Box 1404 Alexandria, Virginia 22313-1404 (703) 836-6620</p>						
			<p style="text-align: center;"></p> <p>SIGNATURE</p> <p>James A. LaBarre</p> <p>NAME</p> <p>28,632</p> <p>REGISTRATION NUMBER</p>			
			<p style="text-align: right;">December 13, 2001</p> <p style="text-align: right;">DATE</p>			

10/018089

3511-4011

14 DEC 2001

Patent
Attorney's Docket No. 032326-179

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of)
Christian LERICHE et al) Group Art Unit: Unassigned
Application No.: Unassigned) Examiner: Unassigned
Filed: December 14, 2001)
For: NOVEL LINEAR)
BIODEGRADABLE COPOLYMER,)
COMPOSITION COMPRISING)
SAME, USE OF SAID COPOLYMER)
AND SAID COMPOSITION)

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:

Prior to examination and the calculation of filing fees, kindly amend the above-identified application as follows:

IN THE SPECIFICATION:

Page 1, immediately following the title appearing on lines 1-3, insert the following:

--This disclosure is based upon French Application No. 99/07552, filed on June 15, 1999 and International Application No. PCT/FR00/01488, filed May 30, 2000, which was published on December 21, 2000 in a language other than English, the contents of which are incorporated herein by reference.

Background of the Invention--

1008089.12401

Page 3, before line 7, insert the following heading:

--Summary of the Invention--

Page 20, between lines 6 and 7, insert the following heading:

--Brief Description of the Drawings--

Page 21, before line 10, insert the following heading:

--Discussion of the Drawings--

Pages 39-40, cancel in their entireties.

Add the following Abstract:


--A novel copolymer contains at least two identical or different monomers. When two components X and Y of the monomer are identical or different, and represent an acid, alcohol, amine or isocyanate group, then at least two monomers have groups capable of reacting with each other when X and Y are identical, or at least one monomer comprises groups capable of reacting with one another when X and Y are different. At least one monomer of each type, when X and Y are identical or different, are combined such that the stoichiometry of the ratio X/Y, calculated to obtain a molar mass and specific end points, enable an extension of a carbon chain. The disclosure also includes a composition comprising the copolymer and the uses of the copolymer and the composition.--

10018089.121401

IN THE CLAIMS:

Kindly replace claims 1-18, as follows.

1. (Amended) A copolymer comprising at least two identical or different monomers, the formula of each monomer being as follows (I):



in which:

a) when X and Y are identical, and represent an acid, alcohol, amine or isocyanate group,

then at least two monomers have groups able to react with each other, and,

at least one of the monomers has the following characteristics:

$$a \geq 1$$


$$b \geq 1$$

$$c + d \geq 0$$

$$e \geq 1$$

and Z can be OH, COOH, an alkyl having 1 to 18 carbon atoms, or any other non-reactive group present during the polymerisation process,

the other monomers being of the same type or of the following formula (II):



b) when X and Y are different and represent, independently of each other, an acid, alcohol, amine or isocyanate group,

then at least one monomer comprises groups able to react with each other, and

at least one of the monomers has the following characteristics:

$$a \geq 1$$

$$b \geq 1$$


$$c + d \geq 0$$

$$e \geq 1$$

1018089.121401

and Z can be OH, COOH, an alkyl having 1 to 18 carbon atoms, or any other non-reactive group present during the polymerisation process,

the other monomers being of the same type or of the following formula (II):



c) at least one monomer of each type when X and Y are identical or different, as defined previously, are combined so that the stoichiometry of the ratio X / Y, calculated so as to obtain a given molar mass and given extremities, permits an elongation of the carbon-containing chain.

2. (Amended) A copolymer according to Claim 1, wherein one of the monomers is citric acid.

3. (Amended) A composition comprising at least one copolymer as defined according to claim 1 and at least one ion chosen from amongst Na⁺, Li⁺, Ca⁺⁺, Mg⁺⁺, Zn⁺⁺ and/or at least one oxide chosen from amongst magnesium oxide, zinc oxide or silicon dioxide so as to strengthen the internal structure of the polymer and thus give a thermoreversible composition.

4. (Amended) A composition according to Claim 3, further comprising gluten and/or starch.

5. (Amended) A composition comprising at least one copolymer as defined according to claim 1, gluten and/or starch.

6. (Amended) A composition according to claim 3 wherein the copolymer is present in a quantity ranging from 50 to 100% by weight with respect to the total weight of the composition.

7. (Amended) A composition according to claim 4 wherein the starch and/or gluten is present in a quantity ranging from 0 to 50% by weight, with respect to the total weight of the composition.

8. (Amended) A composition according to claim 3 further comprising at least one additive chosen from amongst colorants, mineral fillers such as titanium oxide, calcium carbonate, pigments, antioxidants, anti-ultraviolet agents and mixtures thereof.

9. (Amended) The use of the copolymer as defined according to claim 1 as an adhesive.

10018089.121401

10. (Amended) The use of the copolymer as defined according to claim 1 as a printing ink.

11. (Amended) The use of the composition as defined according to claim 3 as an adhesive.

12. (Amended) The use according to Claim 11, wherein the copolymer has a degree of polymerisation ranging from approximately 5 to approximately 25.

13. (Amended) The use of the composition as defined according to claim 3 as a printing ink.

14. (Amended) The use according to Claim 13, wherein the copolymer has a degree of polymerisation ranging from approximately 3 to approximately 20.

15. (Amended) A smart card having a support body comprising the copolymer as defined according to claim 1.

16. (Amended) An electronic label having a support comprising the copolymer as defined according to claim 1.

1013089.121401

17. (Amended) A printable support sheet including the copolymer as defined according to claim 1.

18. (Amended) A toy comprising the copolymer as defined according to claim 1.

Add the following new claims:

19. (New) A composition according to claim 6 wherein the copolymer is present in a quantity ranging from 60% to 90% by weight with respect to the total weight of the composition.

20. (New) A composition according to claim 7, wherein the starch and/or gluten is present in a quantity ranging from 10% to 50% by weight.

21. (New) A composition according to claim 7, wherein the starch and/or gluten is present in a quantity ranging from 20% to 35% by weight.


10018089.121401

REMARKS

Entry of the foregoing amendment is respectfully requested. This amendment is intended to place the claims in a more conventional format and eliminate the multiple dependency of the claims.

Respectfully submitted,

BURNS, DOANE, SWECKER & MATHIS, L.L.P.

By: 
James A. LaBarre
Registration No. 28,632

P.O. Box 1404
Alexandria, Virginia 22313-1404
(703) 836-6620

Date: December 14, 2001


10018039.121404

Application No. Unassigned
 Attorney's Docket No. 032326-179
 Page 1

Attachment to Preliminary Amendment dated December 14, 2001

Marked-up Claims 1-18

1. (Amended) A copolymer comprising at least two identical or different monomers, the formula of [the] each monomer being as follows (I):



in which:

a) when X and Y are identical, and represent an acid, alcohol, amine or isocyanate group,

then at least two monomers have groups able to react with each other, and,

at least one of the monomers has the following characteristics:

$$a \geq 1$$

10018089.121401
 10/12/01 63081001

Attachment to Preliminary Amendment dated December 14, 2001

Marked-up Claims 1-18


$$b \geq 1$$

$$c + d \geq 0$$

$$e \geq 1$$

and Z can be OH, COOH, an alkyl having 1 to 18 carbon atoms, or any other non-reactive group present during the polymerisation process,

the other monomers being of the same type or of the following formula (II):



b) when X and Y are different and represent, independently of each other, an acid, alcohol, amine or isocyanate group,

then at least one monomer comprises groups able to react with each other, and

at least one of the monomers has the following characteristics:

$$a \geq 1$$

$$b \geq 1$$

10013089.121401

Attachment to Preliminary Amendment dated December 14, 2001


Marked-up Claims 1-18

$$c + d \geq 0$$

$$e \geq 1$$

and Z can be OH, COOH, an alkyl having 1 to 18 carbon atoms, or any other non-reactive group present during the polymerisation process,

the other monomers being of the same type or of the following formula (II):



c) at least one monomer of each type when X and Y are identical or different, as defined previously, are combined so that the stoichiometry of the ratio X / Y, calculated so as to obtain a given molar mass and given extremities, permits an elongation of the carbon-containing chain.

2. (Amended) A copolymer according to Claim 1, [characterised in that]
wherein one of the monomers is citric acid.

3. (Amended) A composition comprising at least one copolymer as defined according to [one of Claims 1 or 2] claim 1 and at least one ion chosen from amongst Na⁺,

10018089.121401

Attachment to Preliminary Amendment dated December 14, 2001

Marked-up Claims 1-18

Li + + , Ca + + , Mg + + , Zn + + and/or at least one oxide chosen from amongst magnesium oxide, zinc oxide or silicon dioxide so as to strengthen the internal structure of the polymer and thus give a thermoreversible composition.

4. (Amended) A composition according to Claim 3, [characterised in that it also comprises] further comprising gluten and/or starch.

5. (Amended) A composition comprising at least one copolymer as defined according to [one of Claims 1 or 2] claim 1, gluten and/or starch.

6. (Amended) A composition according to [one of Claims 3 to 5, characterised in that] claim 3 wherein the copolymer is present in a quantity ranging from 50 to 100% by weight with respect to the total weight of the composition[, and preferably 60 to 90%].

7. (Amended) A composition according to [one of Claims 4 or 5, characterised in that] claim 4 wherein the starch and/or gluten is present in a quantity ranging from 0 to 50 % by weight, [preferably 10 to 40 % by weight, and even more preferentially 20 to 35 % by weight] with respect to the total weight of the composition.

10018089.121401

Attachment to Preliminary Amendment dated December 14, 2001

Marked-up Claims 1-18

8. (Amended) A composition according to [one of Claims 3 to 5, characterised in that it also comprises] claim 3 further comprising at least one additive chosen from amongst colorants, mineral fillers such as titanium oxide, calcium carbonate, pigments, antioxidants, anti-ultraviolet agents and mixtures thereof.

9. (Amended) The use of the copolymer as defined according to [one of Claims 1 or 2] claim 1 as an adhesive.

10. (Amended) The use of the copolymer as defined according to [one of Claims 1 or 2] claim 1 as a printing ink.

11. (Amended) The use of the composition as defined according to [one of Claims 3 to 10] claim 3 as an adhesive.

12. (Amended) The use according to Claim 11, [characterised in that] wherein the copolymer has a degree of polymerisation ranging from approximately 5 to approximately 25.

13. (Amended) The use of the composition as defined according to [one of Claims 3 to 10] claim 3 as a printing ink.

10018000-121401

Attachment to Preliminary Amendment dated December 14, 2001

Marked-up Claims 1-18

14. (Amended) The use according to Claim 13, [characterised in that] wherein the copolymer has a degree of polymerisation ranging from approximately 3 to approximately 20.

15. (Amended) A smart card [or the like] having a support body comprising the copolymer as defined according to [one of Claims 1 or 2] claim 1.

16. (Amended) An electronic label having a support comprising the copolymer as defined according to [one of Claims 1 or 2] claim 1.

17. (Amended) A printable support sheet including the copolymer as defined according to [one of Claims 1 or 2] claim 1.

18. (Amended) A toy comprising the copolymer as defined according to [one of Claims 1 or 2] claim 1.

10018089-121401

14/pt/2

A NOVEL BIODEGRADABLE LINEAR COPOLYMER,
A COMPOSITION COMPRISING IT, AND USES OF THE COPOLYMER
AND COMPOSITION

5 The present invention relates to a novel
biodegradable linear copolymer, to a composition
comprising the copolymer, to different uses of this
copolymer and composition, and to different objects
comprising this copolymer.

10 Composite polymers able to degrade biochemically
are already known from the document WO 98/40434. These
polymers consist on the one hand of a first polymer
based on lactic acid monomers and on the other hand a
resin containing a thermoplastic polymer, destructured
15 starch and a plasticiser.

Unfortunately such polymers have the major
drawback of having weak mechanical and thermal
properties. This is because these polymers give

10018089-221401

breakable products because of poor resistance to impact and a glass transition T_g below 80°C .

5 A biodegradable mixture of synthetic polymers and polymers of natural origin is also known from the document US 5 446 078.

10 The synthetic polymers used in this mixture are chosen from amongst non-biodegradable plastics, such as polyolefins, rubbers and polyvinyl chloride. Thus, even if the presence of natural polymers makes it possible to biodegrade the non-biodegradable plastics, the rate of degradation of such a polymer mixture still remains too slow. This type of material also has too many drawbacks vis-à-vis respect for the ecological balance of the environment.

15 Finally, there is also known a thermoplastic aliphatic polyester material, polybutyleneglycolsuccinate, obtained at the end of a chemical reaction between glycols and aliphatic dicarboxylic acids. This material is known by the trade name "Bionolle" and is sold by the company Showa
20 Highpolymer Co Ltd.

However, such a material has the drawback of having a very high molar mass.

25 In addition, a reduction in the biodegradability of a large number of materials already known for being so has unfortunately already been observed, because of the increase in their molecular mass, the increase in the crystalline state, or the significant crosslinking of the molecules in these materials.


10018089.121401

This decrease in biodegradability can be observed, for example, on polyesters of the semi-aromatic type, and even more on aromatic polyesters.

Aliphatic polyurethanes and polyamides also have biodegradability properties which are not insignificant but which still remain less than those of polyesters.

Thus there exists a need to have a new aliphatic copolymer which is quickly and perfectly biodegradable, and which can be obtained easily and at lesser cost by means of conventional monomer polycondensation processes.

The object of the invention is therefore a novel copolymer comprising at least two identical or different monomers, the formula of the monomer being as follows (I):



in which:

a) when X and Y are identical, and represent an acid, alcohol, amine or isocyanate group,


then at least two monomers have X, Y groups able to react with each other,

at least one of the monomers have the following characteristics:

$$\begin{aligned} a &\geq 1 \\ b &\geq 1 \\ c + d &\geq 0 \\ e &\geq 1, \end{aligned}$$

and Z can be OH, COOH, an alkyl having 1 to 18 carbon atoms, or any other unreactive group present during the polymerisation process,

the other monomers being of the same type or of the following formula (II):



b) when X and Y are different and represent, independently of each other, an acid, alcohol, amine or isocyanate group,

then at least one monomer comprises X, Y groups able to react with each other,

at least one of the monomers have the following characteristics:

$$a \geq 1$$

$$b \geq 1$$

$$c + d \geq 0$$

$$e \geq 1,$$

and Z can be OH, COOH, an alkyl having 1 to 18 carbon atoms, or any other unreactive group present during the polymerisation process,

the other monomers being of the same type or of the following formula (II):




c) at least one monomer of each type when X and Y are identical or different, as defined above, are combined so that the stoichiometry of the ratio X/Y,

calculated so as to obtain a given molar mass and given extremities, allows an elongation of the carbon-containing chain.

5 This novel copolymer has the advantage of being 100% biodegradable and having several pendent tertiary OH and COOH groups over the entire length of the carbon-containing chain. The presence of the pendent tertiary acid groups makes it possible to modify the physical properties of the copolymer because of the possibility of forming ion and/or hydrogen bonds. 10 These new bonds confer on it properties of more or less crosslinked lattices.

In addition, the acid groups, put in the presence of monovalent cations or even better bivalent cations, 15 allow the creation of a reinforcing ion structure of the type:



20 Finally, the presence of oxides, such as MgO, during the polymerisation process makes it possible to obtain, with the pendent groups of the copolymer,

structures which are substantially of the same nature as those described above.

5 The bonds formed between the pendent groups of the copolymer according to the invention and the ions and/or oxides make it possible to have a reinforced structure of the thermoplastic type. This type of structure has the great advantage of being completely destroyed during a rise in temperature because of physico-chemical transformations.

10 The ion and/or hydrogen bonds are moreover known for being able to be more easily accessible to bacteria, which can act more effectively in the slow process of biodegradation, whilst the covalent bonds present in the crosslinked polymers of the prior art
15 for their part have a much slower biodegradation kinetics, which extends the duration of degradation accordingly. The variation in the physico-chemical properties of the copolymer of the invention, because of the creation/elimination of ion and/or hydrogen
20 bonds, makes it possible to use it in applications of completely different natures.

Such a copolymer according to the invention also has the advantage of having an accelerated biodegradation kinetics when it is mixed with a natural
25 polymer of the starch type, associated or not with gluten.

Starch and gluten (consisting essentially of amino acids and starch) are known for their biodegradable character. They are also known for being
30 used as co-constituents of synthesised polymers, and

10018089-121401

thus affording a reduction in the cost price and an increase in the synergy of the biodegradation of such a composition.

10018009.121401

5 Finally, it is also known to have to use additives making it possible to make the starch and/or gluten chemically compatible with a synthetic polymer. These additives comprise acid or anhydride groups. Thus the use of a polymer like the one in the invention already comprising COOH, and possibly OH, groups makes 10 it possible to perform compatibility chemical reactions without any supplementary addition of compatibility additives.

15 Finally, a stoichiometric ratio of the starting monomers different from 1/1 makes it possible to obtain a final copolymer range having different molecular masses, and consequently different viscosities. The chemical variation in the chain extremities and the variant in the number of pendent groups on the monomers makes it possible to use the copolymer of the invention 20 differently, equally well for example as an adhesive or as a printing ink.

25 A last advantage of this copolymer is that it has a total cost price appreciably lower than the biodegradable copolymers existing so far. It is approximately 35% to 50% lower in cost.

30 The copolymer of the invention is obtained according to an already known method using a catalyst chosen from amongst compounds of the zirconate or titanate type, such as those sold under the brand name "Tysor" by Dupont de Nemours. It is possible to use,

for example, titanium acetylacetonate, triethanolamine titanate, n-butyl polytitanate, chelated zirconate diethylcitrate and mixtures thereof.

5 The use of such a catalyst makes it possible not only to optimise the colour, which may be yellowish, but in particular to hydrolyse the catalyst at the end of the esterification reaction so as to obtain mineral oxides such as TiO_2 , ZnO_2 , which are inert vis-à-vis a reverse de-esterification reaction which may occur
10 should the catalyst remain active.

1018089-121401
15 The polymerisation process can take place in a conventional reactor or more economically using a "thin-film reactor", in particular in a dual-screw extruder whose length/diameter ratio is calculated so as to make it possible to perform all the manufacturing steps at one go. In particular, such a reactor makes it possible to add the starch and/or gluten lastly before the inactivation of the catalyst, which makes it possible to condense the amino acids present in the
20 gluten in particular as polyamides in order to prevent their subsequent degradation during the transformation step.

 Thus the catalysts used can be either esterification catalysts or amidification catalysts.

25 The polymerisation process can comprise different steps, including the feeding of raw materials, the conveying of these materials, their mixing and the discharge of the condensation water. Other steps can be the addition of starch and/or gluten or the addition

of additives chosen from amongst fillers, colorants and mixtures thereof.

5 The polymerisation reaction can continue subsequently with a step of eliminating the water resulting from the reaction in which the amino acids present in the gluten are transformed into polyamides.

10 The copolymer of the invention resulting from these different manufacturing steps can then be directed to an extrusion/cutting step, the cutting being able to be effected either hot and dry, or in water.

15 Finally, a last step of drying the finished product may be necessary, as known to persons skilled in the art.

20 The nature of the screws and the temperature values used in such a reactor and the location of the different components intended to discharge the volatile reaction by-products are already known from the prior art, and particularly in the industrial manufacture of polyesters, for example of the PET or PBT type.

25 The quantities of water to be eliminated are preferably between approximately 10% and 25%, which is in general easy to achieve with a dual-screw extruder which makes it possible to eliminate up to 40% of residual solvents in the manufacture of polymers known from the state of the art.

30 The degree of polymerisation is adjusted continuously. Preferably, one of the monomers carrying tertiary groups is citric acid. The other monomers can be chosen from amongst the compounds of the prior art,

10018039-121401

preferably using any type of monomer containing at least two primary acids and at least one tertiary group chosen from amongst the alcohol, acid and amine groups and mixtures thereof.

5 The physico-chemical characteristics of the copolymer of the invention can direct the choice of the monomer or monomers used at the start, and their respective concentrations defined, for example, by the stoichiometry or the amount of hydrogen and/or ion
10 bonds. The choice of the monomer can also be a function of the manufacturing cost of the copolymer.

 In so far as the use of ions and oxides can improve the cold mechanical properties of the copolymer of the invention, the amount of monomers containing
15 pendent COOH groups influences the amount of ions or oxides which can be used. In a preferred manner, the amount of these compounds is adjusted according to the amount of pendent COOH group, whilst taking account the amount of hydrogen bonds used.

20 The COOH/(ions and/or oxides) stoichiometric ratio of the copolymer of the invention is preferably close to 1.

 The amount of pendent acid groups has an influence on the amount of ions and oxides to be used
25 during the polymerisation. The variation in these amounts influences the properties of rigidity, flexion or biodegradability which are chosen as a function of the nature of the uses of the copolymer of the invention.

Another object of the invention is a composition which comprises the copolymer described above, combined with at least one ion chosen from amongst Na^+ , Li^+ , Ca^{++} , Mg^{++} , Zn^{++} and/or at least one oxide chosen from amongst magnesium oxide, zinc oxide and silicon dioxide.

The addition of compounds such as divalent ions, permitting the creation of ion bonds within the structure of the copolymer, makes it possible to strengthen its structure, as already explained above.

The phenomenon of biodegradation always goes through a hydrolysis phase. However, the ion bonds, particularly sensitive to this type of degradation, thus facilitate the biodegradation of the copolymer of the invention because of the release of macromolecules principally of the polyester type, which behave in a conventional manner vis-à-vis biodegradation phenomena.

The composition according to the invention as defined above can also comprise starch (linear or branched) and/or gluten (starches + amino acids) or any other type of compound able to react, such as wood dust, wood fibres, cellulose fibres, polyvinylalcohol, ethylenevinylalcohol, polyamides, polyurethanes, functional or compatible polyacrylics, polycarbonates, polymethacrylates, polyacrylates and mixtures thereof.

This starch and/or gluten can also be added directly to the composition, which would comprise solely the copolymer according to the invention, without any divalent ion or oxides.

The copolymer may be present in a quantity ranging from 50% to 100% by weight, and preferably 60%

to 90% by weight, with respect to the total weight of the composition.

The starch and/or gluten can be present in a quantity ranging from 0% to 50% by weight, preferably from 10% to 40% by weight, and even more preferably, and for example for applications of the high-strength copolymer on very thin objects of the smart card type, from 20% to 35% by weight with respect to the total weight of the composition. The adding of polyvinylalcohol or ethylenevinylalcohol can be effected at a low concentration so as to preserve correct biodegradation properties of the copolymer of the invention.

The copolymer according to the invention can have a molecular mass of between approximately 500 and 100,000 according to the conversion rate, preferably between 1000 and 40,000 and even more preferably between 1000 and 10,000.

The composition according to the invention can further comprise at least one additive chosen from amongst colorants, mineral fillers such as titanium oxide, calcium carbonate, pigments, antioxidants, anti-ultraviolet agents and mixtures thereof. The additive can be present in a quantity known from the field of the prior art, which affords a good strength of the manufactured material based on the copolymer of the invention.

The glass transition (T_g) of the copolymer according to the invention, obtained according to the

10018089.121401

conventional methods, can preferably be subambient. The Tg can be modified by adding divalent ions and/or oxides, by varying the stoichiometry parameters, the level of each pendent group, or the proportion of ionic crosslinking or hydrogen bonds. These different variations are known from the prior art.

The addition of ionised elements thus causes the high ionicity of the composition. This high ionicity promotes hydrolysis of the composition over time, and consequently the rapid biodegradability of the copolymer present in the composition.

The addition of compounds known for their rapid biodegradation, such as starch and/or gluten or others of the same type, reinforces the biodegradable feature of the composition of the invention and therefore of the copolymer provided that the degree of substitution of such molecules is less than or equal to 2.2.

Two other objects of the invention are a use of the copolymer according to the invention as an adhesive, and a use as a printing ink.

Finally, another object of the invention is a use of the composition as an adhesive and a use as a printing ink. The copolymer can have a degree of polymerisation ranging from approximately 5 to 25 when it is used in adhesive compositions, and a degree of polymerisation ranging from approximately 3 to 20 when it is used in printing compositions according to the nature and composition of the other elements in the composition.

The invention also relates to a smart card with contact, without contact or comprising both at the same time, to a card similar to smart cards having a support body comprising the copolymer as defined above.

5 Another object of the invention is an electronic label on a toy comprising the copolymer as defined above.

10 Finally a last object of the invention is an impermeable support sheet containing the copolymer as defined above. The printing of such a support sheet is carried out by the methods which are conventional in the field of smart cards.

15 The smart cards can be obtained by means of conventional injection, extrusion or lamination processes. The toys can be obtained by conventional moulding or extrusion.

The composition examples which follow are given solely as an indication and are in no way limitative vis-à-vis the invention.

20 The numerical values are given in numbers of moles.

In each example, the concentration of catalyst is 0.1% of the total number of moles.

EXAMPLE 1: (prior art)

25 - Citric acid 0
- Succinic acid 1
- Butanediol 1

The succinic acid/citric acid and COOH/OH stoichiometric ratios are respectively 100/0 and 1.

The mixture of initial compounds is heated at approximately 200°C for approximately 3 hours. This mixture changes progressively from the colourless state to a pronounced cloudy state.

5 The mixture is then drawn under vacuum for approximately one hour so as to discharge the water formed during the reaction. The final product solidifies over time in the form of a solid homogeneous compound, whitish in colour, whose melting point measured by differential enthalpic analysis is 10
10 approximately 109-110°C with a shoulder at approximately 105°C.

The melting enthalpy is approximately 68 J/g and crystallisation takes place at approximately 74°C.

15 The substance is 3% soluble in hexafluoroisopropanol (HFIP), and remains in the form of blocks in dissolution in acetone in a 50/50 proportion.

20 Only the lower molecular masses seem to be soluble in THF.

The substance resulting from this example has a hydrogen bond rupture glass transition which is invisible or only slightly visible.

25 EXAMPLE 2: (invention)

- Succinic acid	0.9
- Citric acid	0.1
- Butanediol	1

The succinic acid/citric acid and COOH/OH
30 stoichiometric ratios are respectively 90/10 and 1.

The same operating method is used as in Example 1. The substance obtained is slightly more yellowish in colour than that of Example 1, but is in the form of a homogeneous solid whose melting point is approximately 102-103°C.

The substance is 3% soluble in HFIP, but dissolves in a higher proportion in acetone. A whitish solution is obtained.

The substance resulting from this example shows a hydrogen bond rupture transition between 80° and 100°C just before melting.

EXAMPLE 3: (invention)

- Citric acid	1
- Succinic acid	0
- Butanediol	1

The succinic acid/citric acid and COOH/OH stoichiometric ratios are respectively 0/100 and 1.

The same operating method is used as in the previous examples. The final product is much more yellowish because of the interactions existing between the citric acid and n-butyl titanate.

The polymer is much more viscous. Unlike the two substances resulting from the previous examples, the polymer solidifies immediately. It has no melting point in the ambient area at ???°C unlike the two previous ones.

Its solubility in HFIP is identical to that of the other two. The 50/50 mixture in acetone gives a partial solubilisation very quickly, with a gelled

appearance. This substance dissolves completely when the quantity of acetone is increased.

The substance resulting from this example does not exhibit any melting in the regions of substances of the previous examples, but a hydrogen bond rupture transition between 100° and 170°C with a maximum at 130°C.

In conclusion from these three examples, the solubility parameters of a butanediol polysuccinate (Example 1) are completely modified by the introduction of citric acid. The behaviour of the final product (Example 1) is characteristic of a product "crosslinked" by hydrogen bonds [tertiary OH ----- COOH], these bonds rupturing in dilute solvent phase.

This is confirmed by the absence of a melting point (Example 3) and by the reduction in the melting point in Example 2.

The substances resulting from these three examples have a subambient T_g .

According to the proportion of citric acid introduced, there is a partial fusion of the succinate chains which becomes lower and lower, but a physical crosslinking which is stronger and stronger through hydrogen bonds, and a progressive decrease in the value of the melting enthalpy.

The disappearance of the melting point is situated around a composition comprising approximately:

- succinic acid	0.2 mol (14.75 g)
- citric acid	0.2 mol (24 g)
- butanediol	0.4 mol (22.5 g)

For the substances resulting from the above three examples, a significant ester peak is found on the infrared spectra. The presence of the COOH and OH groups (3500 to 3000 cm^{-1}) is very significant in the substance of Example 3, less significant in the substance of Example 2 and very low in the substance of Example 1.

This proves that the citric acid does not react by means of its tertiary OH and COOH functions, but solely by virtue of its primary COOH functions.

Example 4: (invention)

- Citric acid	0.28
- Succinic acid	0.72
- Butanediol	1

Example 5: (invention)

- Citric acid	0.5
- Succinic acid	0.5
- Butanediol	1

The composition of Examples 4 and 5 does not have any melting point.

EXAMPLE 6: (invention)

- copolymer	75%
- gluten	25%

In this mixture a perfect compatibility is found between the polymer and gluten because of the presence of the pendent COOH and OH groups.

This composition, whitish in colour, has a melting point at approximately 103°C .

EXAMPLE 7: (invention)

- copolymer	75%
-------------	-----

- linear starch 25%

In this mixture a perfect compatibility is found between the polymer and gluten because of the presence of the pendent COOH and OH groups.

5 This composition, whitish in colour, has a melting point at approximately 103°C.

BRINGING OUT THE MAIN CHARACTERISTICS OF THE COPOLYMER OF THE INVENTION

10 Five manipulations were made, using citric acid and succinic acid in variable proportions, in a COOH_{total}/OH stoichiometric ratio of 1, and to which butanediol was added.

15 Table I below contains the molar proportions of each of the initial constituents of the above five examples:

Examples	Citric acid	Succinic acid	Butanediol	Stoichiometry
1	0	1	1	1/1
2	0.1	0.9	1	1/1
3	0.28	0.72	1	1/1
4	0.5	0.5	1	1/1
5	1	0	1	1/1

Table I

20 The aim of this study is to produce the infrared spectra of the citric acid, succinic acid and polymers resulting from each manipulation.

The copolymers resulting from each example are all obtained according to the following same operating method:

25 The different monomers and the catalyst are introduced into a glass tube. The whole is placed

1018089.121401

under nitrogen and under stirring, the mixture is heated at 200°C for 3 hours and then vacuum is applied for 1 hour at 200°C.

It can be noted that the higher the concentration of citric acid, the faster the solidification of the final product.

- Figure 1 depicts the infrared spectrum of pure succinic acid on a pellet of KBr,

- Figure 2 depicts the infrared spectrum of pure citric acid,

- Figure 3 depicts the infrared spectrum of butanediol,

- Figure 4 depicts the infrared spectrum of the catalyst, titanium IV butoxide,

- Figure 5 depicts the infrared spectrum of Example 1,

- Figure 6 depicts the infrared spectrum of Example 2,

- Figure 7 depicts the infrared spectrum of Example 3,

- Figure 8 depicts the infrared spectrum of Example 4,

- Figure 9 depicts the infrared spectrum of Example 5,

- Figure 10 depicts the straight lines obtained after calculation of the intensity of the troughs in the zone 2800-3600 cm^{-1} ,

- Figure 11 depicts the curve obtained from the calculations made on the bands situated in the zone 1700-1800 cm^{-1} ,

1002800-12140

- Figure 12 depicts the curve obtained by differential enthalpic analysis of the substance of Example 1,

5 - Figure 13 depicts the curve obtained by differential enthalpic analysis of the substance of Example 2,

- Figure 14 depicts the curve obtained by differential enthalpic analysis of the substances of Examples 3, 4 and 5.

10 Figure 1 shows the presence of the following bands:

- an acid band designated by the general reference 1a divided at $1700-1720\text{ cm}^{-1}$ corresponding to the C=O bond,

15 - several free linked OH bands 2a between 3000 and 3600 cm^{-1} ,

- characteristic bands 3 of alcohol and C=O groups situated at 1200 , 1300 , 1420 cm^{-1} and their corresponding harmonics at 2500 , 2600 cm^{-1} , etc.

20 Figure 2 shows the presence of the following bands:

25 - an acid band 1b much wider than that of succinic acid at $1730-1735\text{ cm}^{-1}$ with two shoulders at around 1680 cm^{-1} and at around 2000 cm^{-1} . This demonstrates the presence of very strong hydrogen bonds,

30 - a free linked OH band 2b between 3000 and 3600 cm^{-1} which is much more intense because of the presence of the (tertiary) OH and COOH pendent groups,

- CH₂ bands 4 embedded in the OH band,
- other much more confused bands 5 (in the form of a solid body) related no doubt to the corresponding presence of hydrogen bonds.

5 Figures 5 to 9 show the changes in the following bands according to the concentration of each constituent:

10 - the linked OH band increases in intensity with the citric acid concentration,
- the ester/acid band is difficult to interpret although very sharp. The definition becomes much more clear when the bands in the concentrated zones, such as 2800-3600 cm⁻¹ and 1700-1800 cm⁻¹, are examined.

15 a) In the zone 2800-3000 cm⁻¹, a very appreciable increase in the bonded OH groups is noted compared with the CH₂ groups, and in particular with respect to the symmetrical CH₂ groups of butanediol, whose concentration remains constant in each example.

20 b) In the zone 1700-1800 cm⁻¹, the differentiation of the esters and acids is sharper:

25 - there exists a very sharp divided acid peak 6 at 1715-1720 cm⁻¹ corresponding to succinic acid, for the substances of Examples 1, 2 and 3, which is scarcely perceptible with the substance of Example 4 and which disappears with Example 5,

- there exists an ester + acid peak 7 which increases between Examples 3, 2 and 1, whilst for Examples 3, 4 and 5 the intensity of this peak remains constant because of the maximum saturation. For equal


saturation, a broadening of the ester bands is however noted as a function of the citric acid concentration.

Different calculations have been made for the 2800-3000 cm^{-1} and 1700-1800 cm^{-1} bands in order to determine the intensity of the OH, COOH and CH_2 peaks. The bands being saturated, the calculation is made on the ratios of the half band lengths.

I - Study of the infrared spectra in the 2800-3600 cm^{-1} region

This study makes it possible to distinguish superimposed broad bands corresponding to the OH, CH_3 - CH_2 - and COOH groups (free and linked by the hydrogen bonds) as well as symmetrical and asymmetric broad CH_2 bands.


The only symmetrical CH_2 bands which the system has are those of butanediol marked by asterisks (*) in the following formula:




Butanediol being in each example always in equal quantities, it thus serves as an internal reference.

When the structure of the final compound formed by polycondensation is examined, several cases can be presented according to the reaction kinetics and the ratio between each constituent.

The copolymer can be represented by the following general formula (I) in the case of an excess of succinic acid with a stoichiometry strictly equal to 1:

Formula (I)

Or by formula (II) in the case of an excess of
 5 citric acid with a stoichiometry strictly equal to 1:

Formula (II)

The presence of an acid extremity and an alcohol
 10 extremity can be noted, the acid extremity being able
 to vary on one monomer as a function of the ratio
 between the two acids. The number of citric and
 succinic extremities is fixed by the proportionality
 rule, the number of alcohol extremities being equal to
 15 the total number of acid extremities for an ideal
 stoichiometry of 1. This rule may be modified if the
 reactivity of the two acid groups is different. This
 is because the monomer which reacts the most quickly
 has less chance of finding its extremities at the chain
 20 end even if it is present in excess. Likewise,
 according to the elongation of the chain of the most
 reactive acid, the stoichiometry may change during the

polymerisation reaction and it is possible to obtain two extremities of identical natures, mainly acid.

Thus, starting from this principle and if the polycondensation mechanism is considered, the total number of acid molecules (and consequently the total number of alcohol molecules) introduced initially can be termed " N_0 ", the number of groups of each type " $2N_0$ " and the number of residual groups at the end of the reaction " N ".

" N " can be equal or odd depending on whether the extremities consist of an acid group or an alcohol group, two acid groups or two alcohol groups.

Tables II and III below are then obtained:

<u>Initial</u>	Citric acid	Succinic acid	Butanediol	Total CH_2	Total acid	Total alcohol	Total ester
Acid extremities	$2N_0 x$	$2N_0(1-x)$	-	-	$2N_0$	-	-
Alcohol extremities	-	-	$2N_0$	-	-	$2N_0$	-
Pendent acid	$N_0 x$	-	-	-	$N_0 x$	-	-
Pendent alcohol	$N_0 x$	-	-	-	-	$N_0 x$	-
Esters	-	-	-	-	-	-	-
CH_2	-	-	-	$2 N_0$	-	-	-
<u>Total</u>				$2 N_0$	$2N_0+N_0x$	$2N_0+N_0x$	O

Table II

Final	Citric acid	Succinic acid	Butanediol	Total CH ₂	Total acid	Total alcohol	Total ester
Acid extremities	N x	N(1-x)	-	-	N	-	-
Alcohol extremities	-	-	N	-	-	N	-
Pendent acid	N _O x	-	-	-	N _O x	-	-
Pendent alcohol	N _O x	-	-	-	-	N _O x	-
Ester	-	-	-	-	-	-	2N _O - N
CH ₂	-	-	2 N _O	2 N _O	-	-	-
Total				2N _O	N+N _O x	N+N _O X	2N _O - N

5 Table III

In infrared spectroscopy, each acid group has its "mark" which makes it possible to identify it from the others. This identification is established by means of the constant " ϵ ". The intensity of the band of this group is determined by the following general formula:

$$1 = \epsilon e [c]$$

15 where " ϵ " is the constant of a precise acid group, " e " is the thickness of the film analysed and $[c]$ the acid group concentration.

20 For the acid and alcohol groups present in the region 2800-3600 cm⁻¹, the ratio of the heights or

10018089.121401

widths of peaks of troughs gives the following formulae:

$$I_{\text{COOH}} = \varepsilon_1 e [\text{COOH}]_{\text{e.c.}} + \varepsilon_3 e [\text{COOH}]_{\text{pendent}} + \varepsilon_2 e [\text{COOH}]_{\text{e.s.}}$$

$$I_{\text{OH}} = \varepsilon_2' e [\text{OH}]_{\text{e.a.}} + \varepsilon_4 e [\text{OH}]_{\text{pendent}}$$

$$I_{\text{CH}_2} = \varepsilon_0 e [\text{CH}_2]$$

Where "e.c." means citric extremity, "e.s." succinic extremity and "e.a." alcohol extremity.

The calculation of the ratios gives:

$$I_{\text{COOH}}/I_{\text{CH}_2} = (\varepsilon_1 N x + \varepsilon_2 N (1-x) + \varepsilon_3 N_0 x) / \varepsilon_0 (2N_0)$$

$$I_{\text{OH}} / I_{\text{CH}_2} = (\varepsilon_2' N + \varepsilon_4 N_0 x) / \varepsilon_0 (2N_0)$$

That is to say

$$I_{\text{COOH}}/I_{\text{CH}_2} = [(\varepsilon_1 - \varepsilon_2) / DP_n 2\varepsilon_0] x + (\varepsilon_0 / 2\varepsilon_0) x + (\varepsilon_2 / DP_n 2\varepsilon_0)$$

$$I_{\text{OH}}/I_{\text{CH}_2} = \varepsilon_2' N / 2\varepsilon_0 N_0 + \varepsilon_4 x / 2\varepsilon_0 = \varepsilon_2' / 2\varepsilon_0$$

The degree of polymerisation " DP_n " is given by the following formula:

$DP_n = 1/f (1/1-\alpha)$ where α is the conversion degree, and f the functionality of the reagents.

α is defined by: $\alpha = [\text{ester}]/\text{number of groups}$

that is to say $\alpha = (2N_0 - N) / 2N_0 = 1 - N / 2N_0$

that is to say $1 - \alpha = N / 2N_0$

If it is assumed that $f = 2$ then

$$DP_n = N_0 / N$$

5

This leads to:

$$I_{\text{COOH}} / I_{\text{CH}_2} = [(\epsilon_1 - \epsilon_2) / DP_n \cdot 2\epsilon_0 + \epsilon_0 / 2\epsilon_0] x + \epsilon_2 / DP_n 2\epsilon_0$$

(curve A)

$$I_{\text{OH}} / I_{\text{CH}_2} = \epsilon_4 x / 2\epsilon_0 = \epsilon'_2 DP_n / 2\epsilon_0 \quad (\text{curve B})$$

10

Curves A and B are depicted in Figure 10. Where there exists an acid extremity and an alcohol extremity each having identical reactivities, the curves of the intensity ratios of the troughs should be straight lines drawn as a function of the proportion of citric acid in the total acids.

15

Should one of the pendent alcohol or acid groups react, the functionality would no longer be 2 but would be a function of x , in which case the curves would no longer be straight lines.

20

Where the two extremities are acids, the slope of the ratio $I_{\text{COOH}} / I_{\text{CH}_2}$ changes, whilst the straight line corresponding to $I_{\text{OH}} / I_{\text{CH}_2} = \epsilon_4 x / 2\epsilon_0$ passes through the origin.

25


It can be noted that these curves are two straight lines, the curve B passing through the origin to within any variations in DP_n and any uncertainties in calculation.

30

It may therefore be assumed that DP_n is always relatively identical to itself, and is therefore a


constant, except if the ratios $(\epsilon_1 - \epsilon_2)/\epsilon_0$ and ϵ_1/ϵ_0 are very different. In this case very high variations in DP_n could result in very small variations in slope; this is the case if $(\epsilon_1 - \epsilon_2)/\epsilon_0$ and ϵ_1/ϵ_0 are very small.

- 5 The hydrogen bonds are mainly of the following type:



This explains the high percentage of free OH groups with a small amount of citric acid, as well as the OH OH bonds.

- 10 With an increasing level of citric acid, three types of hydrogen bond coexist statistically. These bonds are as follows:



- 15 The presence of these three types of bond explains the displacement of the peaks as a function of the level of citric acid and "parasitic" bands such as those situated at 1800 cm^{-1} corresponding to a COOH HOOC bond explained below.
- 20 Having regard to the straight lines A and B obtained in Figure 10, it can be assumed that $\epsilon_4 = \epsilon_2 = \epsilon_1 = \epsilon_3$. Which gives the following mathematical formulae:

$$I_{\text{COOH}}/I_{\text{CH}_2} = \epsilon_3 \times / 2\epsilon_0 + \epsilon_2 \text{DP}_n / 2\epsilon_0 \text{ and,}$$

$$I_{\text{OHtotal}}/I_{\text{CH}_2} = \epsilon_3 \times / 2\epsilon_0$$

$$\text{Giving } I_{\text{OHlinked}}/I_{\text{CH}_2} = \epsilon_3(1-\alpha) \times / 2 \epsilon_0, \text{ and}$$

$$I_{\text{OHfree}}/I_{\text{CH}_2} = \epsilon_3 \alpha \times / 2\epsilon_0$$

5

where α represents the percentage of free OH groups.

All this is validated by the fact that the point $x = 0$ on the curve $I_{\text{OH}}/I_{\text{CH}_2}$ is situated on the curve $I_{\text{COOH}}/I_{\text{CH}_2}$ and by the fact that these two curves are linear.

10 Thus it can be noted that the number of COOH and OH groups remains identical in ratio, except for the extremities, and that the pendent COOH and OH groups do not react during the esterification reaction.

15 II - Study of the infrared spectra in the 1700-1800 cm^{-1} region

Here the half bandwidths are used.

It was noted that citric acid (Figure 2) gives one band at 1730 cm^{-1} and another band at 1640 cm^{-1} , and that
20 succinic acid gives two relatively close bands at $1705-1715 \text{ cm}^{-1}$.

A representation is assumed where the band is divided into a left-hand part and a right-hand part, the left-hand part corresponding to citric acid and esters, and
25 the right-hand part to the superimposition of the esters, tertiary citric acid, primary citric acid and primary succinic acid.

If r represents the ratio of the right-hand half-width to the left-hand half-width, r can be defined by the
30 following formula:

10018089-121401

$$r = [\text{dl ester } \varepsilon_1 + \text{dl ac.cit.tert. } \varepsilon_2 + \text{dl ac.ext. } \varepsilon] / [\text{dl ester } \varepsilon_1 + \text{dl ac.cit. tert. } \varepsilon_2]$$

where:

- "dlester" is the half bandwidth of the ester,
- "dl ac.cit.tert." is the half bandwidth of the tertiary citric acid,
- "dl ac.ext." is the half bandwidth of the acids at the chain extremities.

- 10 The chain extremity is defined by N groups distributed as $N_x + N(1-x)$, where N_x corresponds to citric acid, and $N(1-x)$ to succinic acid.

The esters are defined by $2N_0 - N$, if it is assumed that the esters have equal values.

- 15 The pendent citric acid is defined by N_0x .

It can therefore be written that:

$$r-1 = 2 (\varepsilon_3 N_x + \varepsilon_4 N(1-x)) / (\varepsilon_1 (2N_0 - N) + \varepsilon_2 N_0 x)$$

that is to say $r-1 = 2 (\varepsilon_4 N + (\varepsilon_3 - \varepsilon_4) N_x) / (\varepsilon_1 (2N_0 - N) + \varepsilon_2 N_0 x)$

- 20 The degree of conversion α is defined by the ratio of esters created/acids initially present.

$$\text{That is to say } \alpha = (2N_0 - N) / 2N_0$$

- 25 and the degree of polymerisation can be written:

$$DP_n = 1/f (1 / (1-\alpha)) = 2 N_0 / 2N = N_0 / N$$

The equation $r-1$ then becomes as follows:

$$r-1 = 2(\epsilon_3 - \epsilon_4)N / \epsilon_2 N_0 [(\epsilon_4 / (\epsilon_3 - \epsilon_4)) + x] / ((\epsilon_1 / \epsilon_2) (2 - N/N_0) + x)$$

that is to say again

$$r-1 = (2(\epsilon_3 - \epsilon_4) / \epsilon_2 DP_n) / [(\epsilon_4 / (\epsilon_3 - \epsilon_4)) + x] / ((\epsilon_1 / \epsilon_2) (2 - 1/DP_n) + x]$$

The curve $r-1$ defined as a function of the ratio of moles of citric acid/moles of total acid is shown in Figure 11.

Consequently the relationship is indeed of the type $(a+x)/(b+x)$. It is depicted in Figure 11.

In conclusion, the infrared study demonstrates the following points:

- a) the polycondensation takes place in a linear manner whatever the amount of citric acid at the start,
- b) the level of citric acid is high in proportion to the strength of the hydrogen bonds (the COOH and OH groups are very quickly bonded),
- c) the polymerisation degree values DP_n seem close, and yet the calculations can result in very high variations in values of DP_n for small variations in ratio I, and this as a function of the values of ϵ ,

d) the solubility of the products passes through an optimum at around 28%.

DIFFERENTIAL ENTHALPIC ANALYSIS

5

This analysis shows the progressive disappearance of the melting peak with the progressive increase in the concentration of citric acid between each example 1 to 5.

10

The thermal behaviour of the copolymers in each example can be compared to that of the copolymers of the ethylene-vinylalcohol type where the melting peak disappears when the concentration of vinylalcohol increases, the polyvinylalcohol not melting.

15

The thermal behaviour of these polymers also recalls that of the copolymer blocks.

14. The use according to Claim 13, characterised in that the copolymer has a degree of polymerisation ranging from approximately 3 to 20.

5

15. A smart card or the like having a support body comprising the copolymer as defined according to one of Claims 1 or 2.

10 16. An electronic label having a support comprising the copolymer as defined according to one of Claims 1 or 2.


15 17. A printable support sheet including the copolymer as defined according to one of Claims 1 or 2.

18. A toy comprising the copolymer as defined according to one of Claims 1 or 2.

10018089-121401

CLAIMS

1. A copolymer comprising at least two identical or different monomers, the formula of the monomer being as follows (I):



in which:

a) when X and Y are identical, and represent an acid, alcohol, amine or isocyanate group,


then at least two monomers have groups able to react with each other, and,

at least one of the monomers has the following characteristics:

$a \geq 1$
 $b \geq 1$
 $c + d \geq 0$
 $e \geq 1$

and Z can be OH, COOH, an alkyl having 1 to 18 carbon atoms, or any other non-reactive group present during the polymerisation process,

the other monomers being of the same type or of the following formula (II):



5

b) when X and Y are different and represent, independently of each other, an acid, alcohol, amine or isocyanate group,

10

then at least one monomer comprises groups able to react with each other, and

at least one of the monomers has the following characteristics:

15

$$a \geq 1$$

$$b \geq 1$$

$$c + d \geq 0$$


$$e \geq 1$$

20

and Z can be OH, COOH, an alkyl having 1 to 18 carbon atoms, or any other non-reactive group present during the polymerisation process,

25

the other monomers being of the same type or of the following formula (II):



c) at least one monomer of each type when X and Y are identical or different, as defined previously, are combined so that the stoichiometry of the ratio X / Y, calculated so as to obtain a given molar mass and given
5 extremities, permits an elongation of the carbon-containing chain.

2. A copolymer according to Claim 1, characterised in that one of the monomers is citric acid.

3. A composition comprising at least one copolymer as defined according to one of Claims 1 or 2 and at least one ion chosen from amongst Na⁺, Li⁺⁺, Ca⁺⁺, Mg⁺⁺, Zn⁺⁺ and/or at least one oxide chosen from amongst magnesium
10 oxide, zinc oxide or silicon dioxide so as to strengthen the internal structure of the polymer and thus give a thermoreversible composition.

4. A composition according to Claim 3, characterised in that it also comprises gluten and/or starch.

5. A composition comprising at least one copolymer as defined according to one of Claims 1 or 2, gluten and/or starch.

6. A composition according to one of Claims 3 to 5, characterised in that the copolymer is present in a quantity ranging from 50 to 100% by weight with respect to the total weight of the composition, and preferably
25 60 to 90%.

7. A composition according to one of Claims 4 or 5, characterised in that the starch and/or gluten is present in a quantity ranging from 0 to 50% by weight, preferably 10 to 40% by weight, and even more preferentially 20 to 35% by weight with respect to the total weight of the composition.

8. A composition according to one of Claims 3 to 5, characterised in that it also comprises at least one additive chosen from amongst colorants, mineral fillers such as titanium oxide, calcium carbonate, pigments, antioxidants, anti-ultraviolet agents and mixtures thereof.

9. The use of the copolymer as defined according to one of Claims 1 or 2 as an adhesive.


10. The use of the copolymer as defined according to one of Claims 1 or 2 as a printing ink.


11. The use of the composition as defined according to one of Claims 3 to 10 as an adhesive.


12. The use according to Claim 11, characterised in that the copolymer has a degree of polymerisation ranging from approximately 5 to 25.


13. The use of the composition as defined according to one of Claims 3 to 10 as a printing ink.

10018089.121401













10018089.121401







10018069-12101










10018081001







FIGURE 12

10018089-12






FIGURE 14

COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY (CONT'D)
(Includes Reference to Provisional and International (PCT) Applications)

Attorney's Docket
 No. GEM656

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) or International (PCT) Application(s) designating the United States of America that is/are listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in that/those prior application(s) in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose to the U.S. Patent and Trademark Office all information known to me to be material to the patent ability as defined in Title 37, Code of Federal Regulations § 1.56, which became available between the filing date of the prior application(s) and the national or international filing date of this application:

PRIOR U.S. APPLICATIONS OR INTERNATIONAL (PCT) APPLICATIONS DESIGNATING THE U.S. FOR BENEFIT UNDER 35 U.S.C. § 120:

U.S. APPLICATIONS		STATUS (check one)		
U.S. APPLICATION NUMBER	U.S. FILING DATE	PATENTED	PENDING	ABANDONED
		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PCT APPLICATIONS DESIGNATING THE U.S.				
PCT APPLICATION NO.	PCT FILING DATE	U.S. APPLICATION NUMBERS ASSIGNED (if any)		

I hereby appoint the following attorneys and agent(s) to prosecute said application and to transact all business in the U.S. Patent and Trademark Office connected therewith and to file, prosecute and to transact all business in connection with international applications directed to said invention:

William L. Mathis	17,337	R. Danny Huntington	27,903	Gerald F. Swiss	30,113
Robert S. Swecker	19,885	Eric H. Weisblatt	30,505	Charles F. Wieland III	33,096
Haton N. Mandros	22,124	James W. Peterson	26,057	Bruce T. Wiedner	33,815
Benton S. Duffett, Jr.	22,030	Teresa Slaneck Rea	30,427	Todd R. Walters	34,040
Norman H. Stepano	22,716	Robert E. Krebs	25,885	Ronni S. Jillions	31,979
Ronald L. Grudziecki	24,970	William C. Rowland	30,888	Harold R. Brown III	36,341
Frederick G. Michaud, Jr.	26,003	T. Gene Dillahunty	25,423	Allen R. Baum	36,086
Alan E. Kopecki	25,813	Patrick C. Keane	32,858	Steven M. duBois	35,023
Regis E. Shutter	26,999	B. Jefferson Boggs, Jr.	32,344	Brian P. O'Shaughnessy	32,747
Samuel C. Miller, III	27,360	William H. Benz	25,952	Kenneth B. Leffler	36,075
Robert G. Mukai	28,531	Peter K. Skiff	31,917	Fred W. Hathaway	32,236
George A. Hovanec, Jr.	28,223	Richard J. McGrath	29,195		
James A. LaBarre	28,632	Matthew L. Schneider	32,814		
E. Joseph Gess	28,510	Michael G. Savage	32,596		



21639

and:

Address all correspondence to:

BURNS, DOANE, SWECKER & MATHIS, L.L.P.
 P.O. Box 1404
 Alexandria, Virginia 22313-1404



21639

Address all telephone calls to:

at (703) 836-6620.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY
Includes Reference to Provisional and International (PCT) Applications

Attorney's Docket No.
 GEM656

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name;

BELIEVE I AM THE ORIGINAL, FIRST AND SOLE INVENTOR (IF ONLY ONE NAME IS LISTED BELOW) OR AN ORIGINAL, FIRST AND JOINT INVENTOR (IF PLURAL NAMES ARE LISTED BELOW) OF THE SUBJECT MATTER WHICH IS CLAIMED AND FOR WHICH A PATENT IS SOUGHT ON THE INVENTION ENTITLED:

A novel biodegradable linear copolymer, a composition comprising it, and uses of the copolymer and composition

The specification of which (check only one item below):

- ☐ is attached hereto.
☐ was filed as United States Patent Application Number _____
 on _____

and was amended on _____ (if applicable).

- ☒ was filed as International (PCT) Application Number PCT/FR00/01488
 on May 30th, 2000
 and was amended on December 15th, 2001 (if applicable).

HAVE REVIEWED AND UNDERSTAND THE CONTENTS OF THE ABOVE-IDENTIFIED SPECIFICATION, INCLUDING THE CLAIMS, AS AMENDED BY ANY AMENDMENT REFERRED TO ABOVE.

ACKNOWLEDGE THE DUTY TO DISCLOSE TO THE U.S. PATENT AND TRADEMARK OFFICE ALL INFORMATION KNOWN TO ME TO BE MATERIAL TO PATENTABILITY AS DEFINED IN TITLE 37, CODE OF FEDERAL REGULATIONS, Sec. 1.56 (as amended effective March 16, 1992);

do not know and do not believe the said invention was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to said application; that said invention was not in public use or on sale in the United States of America more than one year prior to said application; that said invention has not been patented or made the subject of an inventor's certificate issued before the date of said application in any country foreign to the United States of America on any application filed by me or my legal representatives or assigns more than six months prior to said application;

hereby claim foreign priority benefits under Title 35, United States Code, §§ 119 (a)-(c) of any foreign application(s) for patent or inventor's certificate or of any International (PCT) Application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application(s) for patent or inventor's certificate or any PCT international (PCT) Application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed:

PRIOR FOREIGN/PCT APPLICATION(S) AND ANY PRIORITY CLAIMS UNDER 35 U.S.C. §119:

COUNTRY (if PCT, Indicate "PCT")	APPLICATION NUMBER	DATE OF FILING (day, month, year)	PRIORITY CLAIMED UNDER 35 U.S.C. §119
France	FR99/07552	15/06/1999	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No
PCT	FR00/01488	30/05/2000	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No
			<input type="checkbox"/> Yes <input type="checkbox"/> No
			<input type="checkbox"/> Yes <input type="checkbox"/> No
			<input type="checkbox"/> Yes <input type="checkbox"/> No

hereby claim the benefit under Title 35, United States Code § 119(e) of any United States provisional application(s) listed below.


APPLICATION NUMBER)

(FILING DATE)

APPLICATION NUMBER)


(FILING DATE)

COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY (CONT'D) (Includes Reference to Provisional and International (PCT) Applications)	Attorney's Docket No GEM656
---	--------------------------------

20 FULL NAME OF SOLE OR FIRST INVENTOR LERICHE Christian	SIGNATURE 	DATE 16/11/2001
---	--	--------------------


RESIDENCE (CITY & STATE/COUNTRY) Ancien chemin de Peynier Les Vaudo Ouest F-TRETS 13530 / France FRX	CITIZENSHIP French
---	-----------------------

POST OFFICE ADDRESS (HOME ADDRESS)

20 FULL NAME OF SECOND JOINT INVENTOR, IF ANY BOCCIA Henri	SIGNATURE 	DATE 16/11/2001
---	--	--------------------

RESIDENCE (CITY & STATE/COUNTRY) Grand Lot F-13720 BELCODENE / France FRX	CITIZENSHIP French
---	-----------------------

POST OFFICE ADDRESS (HOME ADDRESS)

30 FULL NAME OF THIRD JOINT INVENTOR, IF ANY LEMOUSIN Isabelle	SIGNATURE 	DATE 23/11/2001
---	--	--------------------

RESIDENCE (CITY & STATE/COUNTRY) Residence du Parc Mozart - Bt 17 F-13100 AIX EN PROVENCE / France FRX	CITIZENSHIP French
--	-----------------------

POST OFFICE ADDRESS (HOME ADDRESS)


FULL NAME OF FOURTH JOINT INVENTOR, IF ANY	SIGNATURE	DATE
RESIDENCE (CITY & STATE/COUNTRY)	CITIZENSHIP	

POST OFFICE ADDRESS (HOME ADDRESS)

FULL NAME OF FIFTH JOINT INVENTOR, IF ANY	SIGNATURE	DATE
RESIDENCE (CITY & STATE/COUNTRY)	CITIZENSHIP	

POST OFFICE ADDRESS (HOME ADDRESS)

United States Patent & Trademark Office
Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ Page(s) _____ of _____ were not
present
for scanning. (Document title)

*X Scanned copy is best available. Drawings fig. 10, 11
are very dark.*